



PHYSICAL PROPERTIES

Interliner Paper Materials

Specified Properties	Units	Values Specified
Color	-	Brown
Thickness	-	0.12mm (0.005")
Moisture Content	%	8 Max
Moisture content	%	5-9
Water Absorption MD	Mm	10 Min.
Water Absorption CD	Mm	10 Min.
Air Permeability	m/Pa.Sec	0.5 to 1.0
Tensile Index MD	Nm/g	78 Min
Tensile Index CD	Nm/g	28 Min
Elongation MD	%	2.0 Min
Elongation CD	%	4.0 Min
Tear Index MD	mN m ² /g	5 Min
Tear Index CD	mN m ² /g	6 Min
Electric Strength in Air	KV/mm	7.0 Min
Ash Content	%	1.0 Max
Heat Stability (150degC,24hrs)	%	20 Max

MIDWEST DISTRIBUTION CENTER

N534 STATE ROAD 67

ASHIPPUN, WI 53003

CELL: (262) 269-2991

TEL: (920) 355-4171