



ST10

Antistatic Cover Tape for Polystyrene Carrier Tape


CONSTRUCTION: .001" Polyester film (polyethylene terephthalate)
.001" Heat activated adhesive

DESCRIPTION: Clear polyester film coated with heat activated adhesive and anti-static properties.

- BENEFITS:**
- Wide range of sealing temperatures
 - Protects surface mounted components
 - Consistent seal within EIA 481 requirements
 - Stable antistatic properties

TYPICAL PROPERTIES	VALUE	TEST METHOD
Overall Thickness	.0022	ASTM D374
Break Strength	20 lbs/in. width	ASTM D882
Elongation	100% min.	ASTM D882
Width Tolerance	< 65.5 mm nominal +/- 0.10 mm 65.5 mm - 81.5 mm +/- 0.15 mm 82.0 mm - 113.5 mm +/- 0.20 mm 114 mm - 145.5 mm +/- 0.25 mm > 146 mm +/- 0.30 mm	Laser Micrometer
Resistivity (ohm/sq.)	Film Side 1.0×10^{10} Adhesive Side 1.0×10^{10}	ASTM D257
Haze	75% Max.	ASTM D1003-95
Luminous Transmittance	90%	ASTM D1003-95

BOND PROFILE



Equipment: Systemation MT30
Conditions: 32 PSI, .35 Sec.

Base Stock: Polystyrene
Bonds taken after 24 hours, 23°C

RECOMMENDED SEALING CONDITIONS

Temperature	150° - 200° C	Pressure	30 - 40 PSI
Time	.25 - .40 Sec.	Seal Rail Width	.015" - .020"

PLEASE SEE REVERSE SIDE FOR ADDITIONAL INFORMATION



ST10

Antistatic Cover Tape for Polystyrene Carrier Tape

PACKAGING

WIDTHS:	Widths available to fit all standard carrier tapes.
SPLICE FREE LENGTHS:	300 meters +6/-0 500 meters +10/-0
CORES:	3" I.D.
COLOR:	Natural*

*Slight variations which do not affect product performance are normal

STORAGE CONDITIONS

ST10 cover tapes should be stored in a controlled environment. The optimum conditions defined below will yield a shelf life of two years from the manufacturing date found on the core label and ensure the maximum service life of the product.

Temperature: 27°C +/- 10°
Humidity: 50% R.H. +/- 20%

The data presented here are intended for product selection purposes only. NEPTCO reserves the right to improve, enhance, and modify the features and specifications of these products. This data is provided for informational purposes only. Please contact your NEPTCO representative to determine the current product matching your specific requirements.

NEPTCO only warrants that its product will work in a manner consistent with the capabilities for which they were designed. This warranty shall be void if the product has been tampered with or improperly used.

Except for the express warranty and limited remedies described herein, NEPTCO disclaims all other warranties, expressed or implied, including the implied warranty of merchantability and the implied warranty of fitness for a particular purpose.

The Buyer's remedies under the limited warranty stated above shall be limited to a return of the purchase price of the product. NEPTCO and its authorized agents shall not be liable for any other damages including consequential damages, incurred in connection with the use or performance of the product.

NEPTCO, Incorporated
Box 2323, 30 Hamlet Street
Pawtucket, RI 02861-0323 USA
TEL: 401-722-5500
FAX: 401-722-6378
www.neptco.com